

## UV Stabilized Polymer Sheets



### FABRICATOR & SPECIFIER BENEFITS

- Low moisture absorption
- Superior flatness
- Excellent corrosion resistance
- Superior UV stabilization
- Durable finish
- Easily cleaned
- Will not delaminate
- FDA approved for food contact

### APPLICATION AREAS

- Rod holders
- Racks
- Doors
- Cup holders
- Swim platforms
- Hatches
- Cabinetry
- Cutting boards

### COLORS AVAILABLE

- Polar White
- Dolphin Grey
- Glacier Grey
- Seafoam
- Sandshade
- Black

TECHNICAL DATA			
PROPERTY	UNIT	NOMINAL	ASTM
		VALUE	METHOD
Density	g/cm <sup>3</sup>	>0.956	D1505
Tensile Strength @ Break	psi	>4000	D638
Elongation @ Break	%	>600	D638
Flexural Modulus	psi	>200,000	D790
Shore D Hardness	--	68	D2240
Tensile Impact	ft. lbs./in. <sup>2</sup>	>100	D1822
Impact Brittleness Temp.	°F	<50	D746
Vicat Softening Temp.	°F	>250	D1525
Heat Deflection Temp.	°F	>175	D648
Co-efficient of Liner Thermal Expansion	in./in./F	--	7x10 <sup>-5</sup>

### STANDARD AVAILABILITY

Sheet Size . . . . . 54" x 96"  
 Standard Thicknesses .1/4", 3/8", 1/2", 3/4", 1"  
 Tolerances . . . . . Thicknesses: +/- 5%, Length/width: +1/2" - 0"

Boatboard LW Polymer Sheet is available in a lightweight foamed core option.  
 Custom colors, lengths and thicknesses are available. Please call for minimum order requirements.  
 All sheets are stress relieved.

LIMITED WARRANTY: Laminations, Inc. makes NO REPRESENTATIONS OR WARRANTY, EXPRESS OR IMPLIED, concerning its products. Defective products will be replaced or purchase price refunded. Data concerning the physical properties and characteristics of products are subject to variations consistent with the test methods used. They are believed to be accurate, but NO REPRESENTATION OR WARRANTY EXPRESS OR IMPLIED is made concerning such physical properties and characteristics. Each purchaser is responsible to determine the fitness of Laminations' products for its own purposes, and NO WARRANTY is made concerning their application or use for any purpose. LAMINATIONS makes no WARRANTY OR REPRESENTATION concerning any use or application of its products. Each purchaser is solely responsible for insuring that its' use of Laminations' products does not infringe any patents, and no information supplied with Laminations' products should be construed as an offer of indemnity for patent infringement. Nominal values should not be interpreted as specifications.