



**FABRICATOR & SPECIFIER BENEFITS**

- High impact resistance
- Superior low temperature strength
- Lightweight
- Good abrasion resistance
- Matte finish
- Resistant to chipping, breaking, cracking, peeling, splintering, and bending
- Non-absorbent

**APPLICATION AREAS**

- Cutting boards

**OPTIONAL COLORS**

- Red
- Yellow
- Blue
- Green
- Tan
- Black

| TECHNICAL DATA              |                   |                   |        |
|-----------------------------|-------------------|-------------------|--------|
| PROPERTY                    | UNIT              | TYPICAL ASTM TEST |        |
|                             |                   | VALUE             | METHOD |
| Melt Index                  | g/10 min          | 0.29              | D1238  |
| Density                     | g/cm <sup>3</sup> | 0.956             | D1505  |
| Tensile Strength            | psi               | 4,450             | D638   |
| Elongation @ Break          | %                 | 960               | D638   |
| Flexural Modulus            | psi               | 215,000           | D790   |
| Low Temperature Brittleness | °C                | <76               | D747   |
| Vicat Softening Point       | °C                | 131               | D1525  |

**STANDARD AVAILABILITY**

Color . . . . .Natural  
 Sheet Size . . . . .48" x 96", 48" x 120", 60" x 120"  
 Gauge . . . . .7/16", 1/2", 3/4", 5/8", 1"  
 Tolerances . . . . .Gauge: +/- 5%, Length/width: +1/2" - 0"

Custom colors, lengths and thicknesses are available. Please call for minimum order requirements.  
 All sheets are stress relieved.

Approved by: U.S. Department of Agriculture, Canada Department of Agriculture, Meets NSF (National Sanitation Foundation) Specifications

LIMITED WARRANTY: Laminations, Inc. makes NO REPRESENTATIONS OR WARRANTY, EXPRESS OR IMPLIED, concerning its products. Defective products will be replaced or purchase price refunded. Data concerning the physical properties and characteristics of products are subject to variations consistent with the test methods used. They are believed to be accurate, but NO REPRESENTATION OR WARRANTY EXPRESS OR IMPLIED is made concerning such physical properties and characteristics. Each purchaser is responsible to determine the fitness of Laminations' products for its own purposes, and NO WARRANTY is made concerning their application or use for any purpose. LAMINATIONS makes no WARRANTY OR REPRESENTATION concerning any use or application of its products. Each purchaser is solely responsible for insuring that its' use of Laminations' products does not infringe any patents, and no information supplied with Laminations' products should be construed as an offer of indemnity for patent infringement. Nominal values should not be interpreted as specifications.

This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520. Information contained herein is considered accurate to our best knowledge. It is offered for your consideration and is no way to be construed as a warranty of the product's usefulness for the application.